



Zephyro

1. SPECIFICATIONS AND FIELDS OF EMPLOYMENT

An elegant finish which is characterized by the precious metallic reflections and the sandy microns which stand out and give the dark light effect and also a fantastic pearlescent effect. It also give a very pleasant touch and thanks to the special characteristic of ZEPHYRO guarantees an excellent flexibility during the application and creating elegance in a classic and non classic environment, and is also stands out well in modern environments such as public and private places. ZEPHYRO is in flammable and becomes perfectly washable after 3 weeks of application.

2. COMPOSITION

Special emulsion acrylic mix of natural and synthetic micas, sand microns, organic and inorganic pigments, additives.

3. METHOD OF APPLICATION

Surface preparation

Sandpaper, putty and dust any imperfections with STUCCOMURO and apply 1 coat of FISSATIVO UNIVERSALE which should be correctly diluted with water at a ratio of 1:5 fino ad 1:10 depending on the absorbing of the surface. Leave to dry for at least 4 hours and then apply 1 or 2 coats of PRIMER S white or slightly colored, correctly diluted (please consult the Technical data sheet) leave 4 to 5 hours between each application.

Colouring of the product

Each colour in our color chart has different shades, in order to obtain the desired colour add in 2,5 Lt. di ZEPHYRO SILVER o

ZEPHYRO GOLD the quantity of ARTHE CONCENTRATO according to the following chart:

Art. ... E	Art. ... F	Art. ... G	Art. ... H
3 x 70 ml.	1 x 70 ml.	22 ml.	8 ml.

Application

Spread ZEPHYRO non diluted directly with the special DECORA' Trowel in different directions in most cases it is sufficient just one coat to obtain a correct coverage of the entire surface.

4. TECHNICAL DATA

SPECIFIC WEIGHT: 1,104 +/- 5% Kg./Lt-

PACKAGIN: buckets of Lit 2,5
COLOURS: colours from the colour chart.

YIELD: 10 square meters/ lit per coat.

PRESERVATION: 24 months in the intact packages, away from temperature changes.

DRYING: 12 - 24 hours at a temperature of 20°C.

DILUTION: ready to use.

VISCOSITY BROOKFIELD: 4800 cps ± 5% R6 RPM100 at 25°C.

APPLICATION: by brush, roller, ore spray.

HS-CODE: 32091000

5. ITEM OF SPECIFICATIONS

Decorating and protection of the external and internal surfaces with acrylic silicate water repellent and resistant to water vapour, type ZEPHYRO of Spiver srl applied and finished with a special trowel such as DECORA' TROWEL from SPIVER S.r.l. The price includes the equipment and implementation, excluding the

scaffolding sqm.
€.....

NB The above-mentioned data are susceptible of variations. Spiver Ltd. Is not responsible for any negative result depending on the application of the product out of the company's control and on the agents unrelated to the product quality.



Emotion with paint ...

SPIVER s.r.l.

contrada Babbaurra S.S. 122
93100 Caltanissetta (CL)

Tel. +39 0934 57 77 91 Fax +39 0934 58 87 95

www.spiver.it - info@spiver.it